

FILM INSERT HERE

Interior Side

Benefits and selection criteria

- + Rejects up to 77% of solar energy, reducing heat build-up and energy costs
- + Exterior installation provides protection for hard to reach locations
- + Blocks >99% of ultraviolet rays*, helping to protect furnishings by reducing premature fading
- + Silver hue with low interior and high exterior reflectivity
- + Reduces glare and eye fatigue
- + Manufacturer's limited warranty includes five year glass breakage and three year seal failure warranty†

EASTMAN

LLumar.com

*Wavelengths 300-380nm. †Certain restrictions apply; see authorized dealer for warranty details. © 2016 Eastman Chemical Company. VISTA™, the VISTA® logo, LLumar® and the LLumar® logo are trademarks of Eastman Chemical Company or one of its wholly owned subsidiaries. As used herein, ® denotes registered trademark status in the U.S. only. Printed in U.S.A. (05/16) SP1054



FILM INSERT HERE

Exterior Side

Performance data

	% Total Solar Transmittance	% Total Solar Reflectance	% Total Solar Absorbance	% Visible Light Transmittance	% Visible Reflectance (exterior)	% Visible Reflectance (interior)	Winter U-value	Shading Coefficient	% UV Ray Protection (wavelengths 300-380nm)	Emissivity	Solar Heat Gain Coefficient	% Total Solar Energy Reflected	Light-to-Solar Heat Gain Ratio (LSG)	% Summer Solar Heat Gain Reduction	% Winter Heat Loss Reduction	% Glare Reduction
Clear Glass 1/8" (3mm) single pane	83	8	9	90	8	8	1.03	1.00	29	0.84	0.86	14	1.05	-	-	-
RXA35 ER HPR 1/8" (3mm) clear single pane	21	50	29	29	48	45	1.04	0.35	>99	0.72	0.30	70	0.97	65	0	68
Clear Glass 1/8" (3mm) dual pane	70	13	17	81	15	15	0.48	0.88	44	0.84	0.76	24	1.07	-	-	-
RXA35 ER HPR 1/8" (3mm) clear dual pane	19	50	31	27	48	46	0.48	0.28	>99	0.72	0.25	75	1.08	67	0	67
Clear Glass 1/4" (6mm) single pane	77	7	16	88	8	8	1.03	0.94	38	0.84	0.82	18	1.07	-	-	-
RXA35 ER HPR 1/4" (6mm) clear single pane	20	50	30	28	47	43	1.02	0.34	>99	0.72	0.29	71	0.97	65	1	68
Clear Glass 1/4" (6mm) dual pane	61	11	28	79	14	14	0.47	0.81	54	0.84	0.70	30	1.13	-	-	-
RXA35 ER HPR 1/4" (6mm) clear dual pane	16	50	34	26	48	43	0.47	0.26	>99	0.72	0.23	77	1.13	67	0	67

The solar performance data reported for Vista by LLumar architectural window films was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement. All safety and performance data has been measured in accordance with ASTM, ASHRAE, AIMCAL and ANSI standards using NFRC methodology with Lawrence Berkeley National Lab's WINDOW Fenestration Analysis Software. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.